

## Radici Radiflam® S RV300AE (cond.) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

### Material Notes:

Radiflam® S is a range of flame retardant polyamides 6 (PA 6) used for injection molding and extrusion for all applications where high fire resistance is required. Information provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Radiflam-S-RV300AE-cond-Nylon-6.php](http://www.lookpolymers.com/polymer_Radici-Radiflam-S-RV300AE-cond-Nylon-6.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	(Dry)
Water Absorption	3.2 %	3.2 %	initially dry
Moisture Absorption at Equilibrium	0.90 %	0.90 %	initially dry

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	95.0 MPa	13800 psi	
Elongation at Break	1.7 %	1.7 %	
Tensile Modulus	11.4 GPa	1650 ksi	
Charpy Impact Unnotched	3.50 J/cm <sup>2</sup>	16.7 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	5.00 J/cm <sup>2</sup>	23.8 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.00 J/cm <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.30 J/cm <sup>2</sup>	6.19 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	(Dry)
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	
Vicat Softening Point	205 °C	401 °F	50°C/h
	@Load 5.10 kg	@Load 11.2 lb	

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	350 V	350 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China