

## Radici Radilon® A 35E 990 (cond.) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , Unreinforced

### Material Notes:

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Radilon-A-35E-990-cond-Nylon-66.php](http://www.lookpolymers.com/polymer_Radici-Radilon-A-35E-990-cond-Nylon-66.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	(Dry)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	63.0 MPa	9140 psi	
Elongation at Break	30 %	30 %	Nominal
Elongation at Yield	20 %	20 %	
Tensile Modulus	2.30 GPa	334 ksi	
Charpy Impact Unnotched	NB	NB	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.620 J/cm <sup>2</sup>	2.95 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.670 J/cm <sup>2</sup>	3.19 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	600 V	600 V	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**