

Radici Radilon® A RCF3505 (dry) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-A-RCF3505-dry-Nylon-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	
Water Absorption	5.3 %	5.3 %	
Moisture Absorption at Equilibrium	1.2 %	1.2 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	210 MPa	30500 psi	
Elongation at Break	1.8 %	1.8 %	
Tensile Modulus	21.7 GPa	3150 ksi	
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	5.30 J/cm ²	25.2 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.750 J/cm ²	3.57 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	
Deflection Temperature at 0.46 MPa (66 psi)	245 °C	473 °F	
Deflection Temperature at 1.8 MPa (264 psi)	235 °C	455 °F	
Vicat Softening Point	235 °C	455 °F	50°C/h
	@Load 5.10 kg	@Load 11.2 lb	

Thermal Properties	Metric	English	Comments
Flammability, UL94	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1000 ohm-cm	1000 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China