

## Radici Radilon® A RV150 (cond.) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Radilon-A-RV150-cond-Nylon-66.php](http://www.lookpolymers.com/polymer_Radici-Radilon-A-RV150-cond-Nylon-66.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	(Dry)
Water Absorption	7.9 %	7.9 %	initially dry
Moisture Absorption at Equilibrium	2.3 %	2.3 %	initially dry
Viscosity Measurement	145	145	cm <sup>3</sup> /g Viscosity Number

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	85.0 MPa	12300 psi	
Elongation at Break	13 %	13 %	Nominal
Elongation at Yield	4.9 %	4.9 %	
Tensile Modulus	3.90 GPa	566 ksi	
Charpy Impact Unnotched	3.70 J/cm <sup>2</sup>	17.6 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	7.50 J/cm <sup>2</sup>	35.7 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.590 J/cm <sup>2</sup>	2.81 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.850 J/cm <sup>2</sup>	4.04 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	

Electrical Properties	Metric	English	Comments
Surface Resistance	$1.00e+14$ ohm	$1.00e+14$ ohm	
Comparative Tracking Index	550 V	550 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China