

Radici Radilon® A RV250 (cond.) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-A-RV250-cond-Nylon-66.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	110 MPa	16000 psi	
Elongation at Break	3.8 %	3.8 %	
Tensile Modulus	6.50 GPa	943 ksi	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	550 V	550 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China