

Radici Radilon® A RV350 (cond) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-A-RV350-cond-Nylon-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	(Dry)
Water Absorption	6.3 %	6.3 %	initially dry
Moisture Absorption at Equilibrium	1.5 %	1.5 %	initially dry
Viscosity Measurement	145	145	cm ³ /g Viscosity Number

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	
Elongation at Break	3.3 %	3.3 %	
Tensile Modulus	9.90 GPa	1440 ksi	
Charpy Impact Unnotched	5.90 J/cm ²	28.1 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	9.00 J/cm ²	42.8 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.900 J/cm ²	4.28 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	

Electrical Properties Comparative Tracking Index	Metric 350 V	English 500 V	Comments
---	-----------------	------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China