

## Radici Radilon® A RV350 (dry) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Radilon-A-RV350-dry-Nylon-66.php](http://www.lookpolymers.com/polymer_Radici-Radilon-A-RV350-dry-Nylon-66.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	
Water Absorption	6.3 %	6.3 %	
Moisture Absorption at Equilibrium	1.5 %	1.5 %	
Viscosity Measurement	145	145	cm <sup>3</sup> /g Viscosity Number

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	195 MPa	28300 psi	
Elongation at Break	3.1 %	3.1 %	
Tensile Modulus	11.9 GPa	1730 ksi	
Charpy Impact Unnotched	8.50 J/cm <sup>2</sup>	40.4 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	10.0 J/cm <sup>2</sup>	47.6 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.850 J/cm <sup>2</sup>	4.04 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.10 J/cm <sup>2</sup>	5.23 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	
Deflection Temperature at 0.46 MPa (66 psi)	255 °C	491 °F	
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	

Thermal Properties	245 °C Metric	473 °F English	Comments
	@Load 5.10 kg	@Load 11.2 lb	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00 \times 10^{11}$ ohm-cm	$\geq 1.00 \times 10^{11}$ ohm-cm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China