

## Radici Radilon® A USZ200 (cond.) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Radilon-A-USZ200-cond-Nylon-66.php](http://www.lookpolymers.com/polymer_Radici-Radilon-A-USZ200-cond-Nylon-66.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	(Dry)
Water Absorption	7.3 %	7.3 %	initially dry
Moisture Absorption at Equilibrium	1.9 %	1.9 %	initially dry

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.0 MPa	3630 psi	
Elongation at Break	>= 50 %	>= 50 %	Nominal
Elongation at Yield	30 %	30 %	
Tensile Modulus	0.850 GPa	123 ksi	
Charpy Impact Unnotched	NB	NB	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	8.50 J/cm <sup>2</sup>	40.4 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	12.0 J/cm <sup>2</sup>	57.1 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	

Electrical Properties Comparative Tracking Index	Metric 500 V	English 500 V	Comments
---	-----------------	------------------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China