

Radici Radilon® S 38F (cond.) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Radilon® S is a range of polyamide 6 (PA6) products obtained through the polymerization of caprolactam and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-S-38F-cond-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	(Dry)
Water Absorption	11 %	11 %	initially dry
Moisture Absorption at Equilibrium	3.1 %	3.1 %	initially dry
Viscosity Measurement	225	225	cm ³ /g Viscosity Number

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	40.0 MPa	5800 psi	
Elongation at Break	>= 50 %	>= 50 %	Nominal
Elongation at Yield	30 %	30 %	
Tensile Modulus	1.10 GPa	160 ksi	
Charpy Impact Unnotched	NB	NB	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China