

Radici Radilon® S CP400 (cond.) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Radilon® S is a range of polyamide 6 (PA6) products obtained through the polymerization of caprolactam and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-S-CP400-cond-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.47 g/cc	1.47 g/cc	(Dry)
Water Absorption	5.8 %	5.8 %	initially dry
Moisture Absorption at Equilibrium	1.9 %	1.9 %	initially dry

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	
Elongation at Break	30 %	30 %	Nominal
Elongation at Yield	17 %	17 %	
Tensile Modulus	2.60 GPa	377 ksi	
Charpy Impact Unnotched	7.00 J/cm ²	33.3 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	8.50 J/cm ²	40.4 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.300 J/cm ²	1.43 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.550 J/cm ²	2.62 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	

Electrical Properties Comparative Tracking Index	Metric 350 V	English 500 V	Comments
---	-----------------	------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China