

Radici Radilon® SHS (dry) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

General Purpose Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-SHS-dry-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	75.0 MPa	10900 psi	ISO 527-1/2
Elongation at Break	>= 50 %	>= 50 %	ISO 527-1/2
Elongation at Yield	4.1 %	4.1 %	ISO 524-1/2
Tensile Modulus	3.05 GPa	442 ksi	ISO 527-1/2
Flexural Strength	95.0 MPa	13800 psi	ISO 178
Flexural Modulus	2.35 GPa	341 ksi	ISO 178
Charpy Impact, Notched	0.620 J/cm ²	2.95 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 1135 7-1-3
Deflection Temperature at 1.8 MPa (264 psi)	55.0 °C	131 °F	ISO 75/2Af
Vicat Softening Point	190 °C	374 °F	ISO 306
Flammability, UL94	V-2 @Thickness 0.800 mm	V-2 @Thickness 0.0315 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China