

Radici Raditer® B RV 150 Polybutylene Terephthalate with 15% Glass fiber

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 10% Glass Fiber Filled

Material Notes:

Raditer® B RV 150 is a glass fiber reinforced thermoplastic polyester based on polybutylene terephthalate. The PBT compounds combine excellent thermal, mechanical, electrical and chemical properties with very good dimensional stability. Suggestions for application:

Technical items with a wide range of stiffness. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Raditer-B-RV-150-Polybutylene-Terephthalate-with-15-Glass-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ISO 1183
Moisture Absorption at Equilibrium	0.18 %	0.18 %	ISO 62

Mechanical Properties	Metric	English	Comments
Elongation at Break	100 %	100 %	ISO 527-2/1A
Tensile Modulus	6.20 GPa	899 ksi	ISO 527-2/1A
Flexural Strength	150 MPa	21800 psi	ISO 178/1A
Flexural Modulus	4.50 GPa	653 ksi	ISO 178/1A
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	ISO 179 eU
Charpy Impact, Notched	0.650 J/cm ²	3.09 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	ISO 11357-1-3
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75-2/Af
Deflection Temperature at 1.8 MPa (264 psi)	185 °C	365 °F	ISO 75-2/Af
Vicat Softening Point	200 °C @Load 5.10 kg	392 °F @Load 11.2 lb	50°C/h; ISO 306/B50
Flammability, UL94	HB @Thickness 0.800 mm	HB @Thickness 0.0315 in	
Glow Wire Test	700 °C @Thickness 2.00 mm	1290 °F @Thickness 0.0787 in	CEI 695-2-1/2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China