

## Radici Raditer® B RVA 200 Polybutylene Terephthalate with 20% Glass fiber

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

### Material Notes:

Raditer® B RVA is a range of glass fiber reinforced Polybutylene terephthalate blends for injection molding, with excellent dimensional stability, low warpage and good surface aspect. Information provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Raditer-B-RVA-200-Polybutylene-Terephthalate-with-20-Glass-fiber.php](http://www.lookpolymers.com/polymer_Radici-Raditer-B-RVA-200-Polybutylene-Terephthalate-with-20-Glass-fiber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	ISO 62
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Elongation at Break	110 %	110 %	ISO 527-2/1A
Tensile Modulus	7.00 GPa	1020 ksi	ISO 527-2/1A
Flexural Strength	155 MPa	22500 psi	ISO 178/1A
Flexural Modulus	5.50 GPa	798 ksi	ISO 178/1A
Charpy Impact Unnotched	5.50 J/cm <sup>2</sup>	26.2 ft-lb/in <sup>2</sup>	ISO 179 eU
Charpy Impact, Notched	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	ISO 11357-1-3
Deflection Temperature at 0.46 MPa (66 psi)	205 °C	401 °F	ISO 75-2/Af
Deflection Temperature at 1.8 MPa (264 psi)	165 °C	329 °F	ISO 75-2/Af
Vicat Softening Point	145 °C @Load 5.10 kg	293 °F @Load 11.2 lb	50°C/h; ISO 306/B50
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China