

Ravago Manufacturing Americas Echo® RPEHDW NAT (Injection) HDPE

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

Material Notes:

Available in North America Recycled Content: Yes Color: Natural Form: Pellets Processing Method: Injection Molded Information provided by Entec

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ravago-Manufacturing-Americas-Echo-RPEHDW-NAT-Injection-HDPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 - 0.955 g/cc	0.950 - 0.955 g/cc	ASTM D792
Melt Flow	4.0 - 8.0 g/10 min @Load 2.16 kg, Temperature 190 °C	4.0 - 8.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	24.8 MPa	3600 psi	ASTM D638
Flexural Modulus	0.965 GPa	140 ksi	ASTM D790

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China