

Ravago Manufacturing Americas Hybrid B3030 Polycarbonate + PBT Alloy

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Entec's proprietary products include a full range of compounds in the Nylon 6/6, Nylon 6, ABS, PBT, Polycarbonate, PC/ABS, PC/ASA, PC/PBT, and PPO/PPE resin families. Information provided by Ravago.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ravago-Manufacturing-Americas-Hybrid-B3030-Polycarbonate-PBT-Alloy.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ASTM D792
Melt Flow	32 g/10 min @Load 5.00 kg, Temperature 260 °C	32 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	63.4 MPa	9200 psi	ASTM D638
Flexural Yield Strength	96.5 MPa	14000 psi	ASTM D790
Flexural Modulus	2.48 GPa	360 ksi	ASTM D790
Izod Impact, Notched	6.94 J/cm	13.0 ft-lb/in	73°F, 0.125 in; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	106 °C	222 °F	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	243 - 266 °C	470 - 510 °F	
Middle Barrel Temperature	249 - 271 °C	480 - 520 °F	
Front Barrel Temperature	254 - 277 °C	490 - 530 °F	
Nozzle Temperature	254 - 271 °C	490 - 520 °F	
Mold Temperature	65.6 - 87.8 °C	150 - 190 °F	
Drying Temperature	110 °C	230 °F	
Dry Time	4 - 6 hour	4 - 6 hour	
Shot Size	50 - 80 %	50 - 80 %	

Processing Properties	Metric ⁵⁰ rpm	English ⁵⁰ rpm	Comments
-----------------------	--------------------------	---------------------------	----------

Descriptive Properties	Value	Comments
------------------------	-------	----------

Injection Rate	Moderate	
----------------	----------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China