

## Ravago Manufacturing Americas Hybrid S466 ABS + Polycarbonate Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

### Material Notes:

Entec's proprietary products include a full range of compounds in the Nylon 6/6, Nylon 6, ABS, PBT, Polycarbonate, PC/ABS, PC/ASA, PC/PBT, and PPO/PPE resin families. Information provided by Ravago.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ravago-Manufacturing-Americas-Hybrid-S466-ABS-Polycarbonate-Alloy.php](http://www.lookpolymers.com/polymer_Ravago-Manufacturing-Americas-Hybrid-S466-ABS-Polycarbonate-Alloy.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.10 %	0.10 %	24 hrs; ASTM D570
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	0.125 in; ASTM D955
Melt Flow	2.8 g/10 min	2.8 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	
	6.2 g/10 min	6.2 g/10 min	
	@Load 2.16 kg, Temperature 260 °C	@Load 4.76 lb, Temperature 500 °F	ASTM D1238
	12.8 g/10 min	12.8 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 260 °C	@Load 8.38 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	56.5 MPa	8200 psi	ASTM D638
Tensile Strength, Yield	59.3 MPa	8600 psi	ASTM D638
Elongation at Break	70 %	70 %	ASTM D638
Flexural Yield Strength	68.9 MPa	10000 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	8.01 J/cm	15.0 ft-lb/in	73°F, 0.125 in; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	115 °C	239 °F	Unannealed (0.125 in); ASTM D648
Flammability, UL94	HB	HB	0.0590 in

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	232 - 243 °C	450 - 470 °F	
Middle Barrel Temperature	238 - 249 °C	460 - 480 °F	
Front Barrel Temperature	243 - 254 °C	470 - 490 °F	
Nozzle Temperature	249 - 260 °C	480 - 500 °F	
Mold Temperature	60.0 - 82.2 °C	140 - 180 °F	
Drying Temperature	104 °C	220 °F	
Dry Time	3 - 4 hour	3 - 4 hour	
Moisture Content	<= 0.020 %	<= 0.020 %	
Injection Pressure	6.89 - 11.7 MPa	1000 - 1700 psi	
Shot Size	40 - 80 %	40 - 80 %	
Screw Speed	40 - 60 rpm	40 - 60 rpm	

Descriptive Properties	Value	Comments
Injection Rate	Moderate	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China