

## Ravago Manufacturing Americas Hylex® P1010G10FRMA Polycarbonate, 10% Glass Filled

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 10% Glass Filled

### Material Notes:

Polycarbonate, 10% Glass Filled, Flame Retardant Information provided by Ravago.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ravago-Manufacturing-Americas-Hylex-P1010G10FRMA-Polycarbonate-10-Glass-Filled.php](http://www.lookpolymers.com/polymer_Ravago-Manufacturing-Americas-Hylex-P1010G10FRMA-Polycarbonate-10-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm @Thickness 3.17 mm	0.0020 - 0.0050 in/in @Thickness 0.125 in	ASTM D955
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	83.0 MPa	12000 psi	ASTM D638
Elongation at Break	10 %	10 %	ASTM D638
Flexural Strength	124 MPa	18000 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	146 °C	295 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	143 °C	290 °F	ASTM D648
Vicat Softening Point	154 °C	310 °F	ASTM D1525
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	
	V-0 - 5VA @Thickness 3.00 mm	V-0 - 5VA @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Dielectric Strength	16.9 kV/mm	430 kV/in	ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China