

Ravago Manufacturing Americas Hylon® N1000EHL Nylon 6/6 (DAM) (discontinued **)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized

Material Notes:

Information provided by Ravago.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ravago-Manufacturing-Americas-Hylon-N1000EHL-Nylon-66-DAM-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Water Absorption	1.3 %	1.3 %	24 hrs; ASTM D570
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	0.125 in; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	85	85	ASTM D785
Tensile Strength at Break	82.7 MPa	12000 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Strength	114 MPa	16500 psi	ASTM D790
Flexural Modulus	3.03 GPa	440 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	73°F; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	82.8 µm/m-°C	46.0 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	238 °C	460 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	87.8 °C	190 °F	Unannealed; ASTM D648
Flammability, UL94	V-2	V-2	0.0280 in, ALL
	V-2	V-2	0.0591 in, ALL
	V-2	V-2	0.118 in, ALL

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.00e+15 ohm-cm Metric	1.00e+15 ohm-cm English	ASTM D257 Comments
Dielectric Constant	3.7 @Frequency 100 Hz	3.7 @Frequency 100 Hz	ASTM D150
Dielectric Strength	22.6 kV/mm	575 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Melt Temperature	271 - 293 °C	520 - 560 °F	
Mold Temperature	48.9 - 93.3 °C	120 - 200 °F	
Drying Temperature	73.9 °C	165 °F	
Dry Time	2 - 4 hour	2 - 4 hour	
Moisture Content	0.20 %	0.20 %	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Screw Speed	40 - 140 rpm	40 - 140 rpm	

Descriptive Properties	Value	Comments
Holding Pressure	400 to 1400 psi	
Injection Rate	Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China