

Ravago Manufacturing Americas Hylon® N1000THL Nylon 6/6 (DAM)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized

Material Notes:

Information provided by Ravago.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ravago-Manufacturing-Americas-Hylon-N1000THL-Nylon-66-DAM.php

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	94	94	ASTM D785
Tensile Strength at Break	46.2 MPa	6700 psi	ASTM D638
Elongation at Break	130 %	130 %	ASTM D638
Flexural Strength	34.5 MPa	5000 psi	ASTM D790
Flexural Modulus	0.896 GPa	130 ksi	ASTM D790
Izod Impact, Notched	2.14 J/cm	4.00 ft-lb/in	73°F; ASTM D256

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	0.0591 in, BK
	HB	HB	0.118 in, BK

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	ASTM D257
Dielectric Constant	5.8 @Frequency 100 Hz	5.8 @Frequency 100 Hz	ASTM D150

Processing Properties	Metric	English	Comments
Melt Temperature	277 - 293 °C	530 - 560 °F	
Mold Temperature	48.9 - 93.3 °C	120 - 200 °F	
Drying Temperature	73.9 °C	165 °F	
Dry Time	2 - 4 hour	2 - 4 hour	
Moisture Content	0.18 %	0.18 %	
Back Pressure	0.138 - 0.414 MPa	20.0 - 60.0 psi	
Screw Speed	40 - 120 rpm	40 - 120 rpm	

Processing Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China