

## Ravago Manufacturing Americas Hylon® N2040MHL Nylon 6 (Cond)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Heat Stabilized

**Material Notes:**

Information provided by Ravago.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ravago-Manufacturing-Americas-Hylon-N2040MHL-Nylon-6-Cond.php](http://www.lookpolymers.com/polymer_Ravago-Manufacturing-Americas-Hylon-N2040MHL-Nylon-6-Cond.php)

Physical Properties	Metric	English	Comments
Density	1.49 g/cc	0.0538 lb/in <sup>3</sup>	DAM; ASTM D792
Water Absorption	1.1 %	1.1 %	24 hrs, DAM; ASTM D570
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	0.125 in, DAM; ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	51.7 MPa	7500 psi	ASTM D638
Flexural Strength	75.8 MPa	11000 psi	ASTM D790
Flexural Modulus	2.69 GPa	390 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm	1.40 ft-lb/in	73°F; ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	260 - 282 °C	500 - 540 °F	
Mold Temperature	71.1 - 98.9 °C	160 - 210 °F	
Drying Temperature	73.9 °C	165 °F	
Dry Time	2 - 4 hour	2 - 4 hour	
Moisture Content	0.18 %	0.18 %	
Back Pressure	0.138 - 0.414 MPa	20.0 - 60.0 psi	
Screw Speed	50 - 120 rpm	50 - 120 rpm	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China