

Reliance Industries 57-11 Polyvinyl Chloride

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

Material Notes:

Information provided by Reliance Industries Applications: Rigid injection Rigid extrusion Rigid calendaring blow molding

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reliance-Industries-57-11-Polyvinyl-Chloride.php

Physical Properties	Metric	English	Comments
Bulk Density	0.480 - 0.540 g/cc	0.0173 - 0.0195 lb/in ³	PVCH/QCD/3516
Particle Mesh Size	40 Mesh	40 Mesh	Traces; PVCH/QCD/3514
	60 Mesh	60 Mesh	5% Retention; PVCH/QCD/3514
	140 Mesh	140 Mesh	50% Retention; PVCH/QCD/3514
Collected Volatile Condensable Material	<= 0.00030 %	<= 0.00030 %	PVCH/QCD/3520

Descriptive Properties	Value	Comments
Fish Eye count, No.	10	RILH/QA(P)/3782
Heat Loss, %(max.)	0.3	PVCHQCD/3513
K-Value	57	PVCH/QCD/3512; 1% in cyclohexanone at 30°C
Porosity DOP Absorption, ml/g	0.24-0.36	PVCH/QCD/3515

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China