

Reliance Industries LLDPE film - Active alumina + zeolite based film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

Material Notes:

Information provided by Reliance Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reliance-Industries-LLDPE-film-Active-alumina-zeolite-based-film.php

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	460 %	460 %	
Film Elongation at Break, TD	540 %	540 %	
Elmendorf Tear Strength, MD	6.70 g/micron	170 g/mil	
Elmendorf Tear Strength, TD	7.50 g/micron	191 g/mil	
Dart Drop	5.00 g/micron	127 g/mil	
Film Tensile Strength at Break, MD	21.0 MPa	3050 psi	
Film Tensile Strength at Break, TD	19.0 MPa	2760 psi	

Optical Properties	Metric	English	Comments
Haze	55 %	55 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China