

Reliance Industries LLDPE film - Inorganic salt based film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

Material Notes:

Information provided by Reliance Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reliance-Industries-LLDPE-film-Inorganic-salt-based-film.php

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	510 %	510 %	
Film Elongation at Break, TD	620 %	620 %	
Elmendorf Tear Strength, MD	7.00 g/micron	178 g/mil	
Elmendorf Tear Strength, TD	19.0 g/micron	483 g/mil	
Dart Drop	4.60 g/micron	117 g/mil	
Film Tensile Strength at Break, MD	23.0 MPa	3340 psi	
Film Tensile Strength at Break, TD	16.0 MPa	2320 psi	

Optical Properties	Metric	English	Comments
Haze	44 %	44 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China