

Reliance Industries LLDPE film - Organic acid based film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

Material Notes:

Information provided by Reliance Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reliance-Industries-LLDPE-film-Organic-acid-based-film.php

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	600 %	600 %	
Film Elongation at Break, TD	700 %	700 %	
Elmendorf Tear Strength, MD	5.60 g/micron	142 g/mil	
Elmendorf Tear Strength, TD	22.0 g/micron	559 g/mil	
Dart Drop	5.30 g/micron	135 g/mil	
Film Tensile Strength at Break, MD	36.0 MPa	5220 psi	
Film Tensile Strength at Break, TD	34.0 MPa	4930 psi	

Optical Properties	Metric	English	Comments
Haze	53 %	53 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China