

Reliance Industries PBT - 35% Glass filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 40% Glass Fiber Filled

Material Notes:

Information provided by Reliance Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reliance-Industries-PBT-35-Glass-filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.59 g/cc	1.59 g/cc	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	103 MPa	14900 psi	
Tensile Modulus	8.27 GPa	1200 ksi	
Flexural Strength	193 MPa	28000 psi	
Flexural Modulus	8.27 GPa	1200 ksi	
Izod Impact, Notched	6.99 J/cm	13.1 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	218 °C	424 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China