

Reliance Industries Polypropylene - Wollastonite filled

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Information provided by Reliance Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reliance-Industries-Polypropylene-Wollastonite-filled.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	31.0 MPa	4500 psi	
Flexural Strength	46.0 MPa	6670 psi	
Flexural Modulus	<= 4.10 GPa	<= 595 ksi	
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	81.0 °C	178 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China