

## Reliance Industries Relene F56003 Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

### Material Notes:

Relene F56003 is a High Density Polyethylene grade suitable for producing blown parts with excellent drawdown and paper like feel. It is recommended for making carrier bags and coextruded film structures. Information provided by Reliance Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Reliance-Industries-Relene-F56003-Polyethylene.php](http://www.lookpolymers.com/polymer_Reliance-Industries-Relene-F56003-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.956 g/cc	0.0345 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	0.30 g/10 min @Load 2.16 kg	0.30 g/10 min @Load 4.76 lb	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	35.0 MPa	5080 psi	ASTM D882
Film Tensile Strength at Yield, TD	37.0 MPa	5370 psi	ASTM D882
Film Elongation at Break, MD	700 %	700 %	ASTM D882
Film Elongation at Break, TD	900 %	900 %	ASTM D882
Elmendorf Tear Strength, MD	0.700 g/micron	17.8 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	10.0 g/micron	254 g/mil	ASTM D1922
Dart Drop	1.60 g/micron	40.6 g/mil	38mm Dart, 66mm height; ASTM D1709
Film Tensile Strength at Break, MD	55.0 MPa	7980 psi	ASTM D882
Film Tensile Strength at Break, TD	50.0 MPa	7250 psi	ASTM D882

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China