

## Reliance Industries Repol C015EG Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

### Material Notes:

REPOL Polypropylene C015EG is manufactured using Unipol PP process which combines the production efficiency of gas phase fluidized bed reactor technology with the high activity stereospecific catalyst system. Repol C015EG is recommended for use in blow molding and extrusion processes where high impact strength is required. It is an ideal material for making blow molded containers, sheets, automotive trims etc. Features: Consistent processability Good stiffness-impact balance Good surface gloss Information provided by Reliance Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Reliance-Industries-Repol-C015EG-Polypropylene.php](http://www.lookpolymers.com/polymer_Reliance-Industries-Repol-C015EG-Polypropylene.php)

Physical Properties	Metric	English	Comments
Melt Flow	1.5 g/10 min @Load 2.16 kg, Temperature 230 °C	1.5 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.5 MPa	3840 psi	50mm/min; ASTM D638
Elongation at Yield	11 %	11 %	50mm/min; ASTM D638
Flexural Modulus	1.00 GPa	145 ksi	1% secant; ASTM D790A
Izod Impact, Notched	2.25 J/cm @Temperature 23.0 °C	4.22 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China