

## Reliance Industries Repol R110MK Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

### Material Notes:

REPOL Polypropylene R110MK is manufactured using Unipol PP process which combines the production efficiency of gas phase fluidized bed reactor technology with the high activity stereospecific catalyst system. Repol R110MK is recommended for use in injection molding processes. It is an ideal material for attaining high clarity in houseware and industrial products. This grade is recommended for non food contact applications. Repol R110MK contains clarifier and antistatic agent that reduces static charge buildup on products. Features: Consistent processability Good clarity Superior mechanical properties Low static charge build-up and reduced dust pickup Information provided by Reliance Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Reliance-Industries-Repol-R110MK-Polypropylene.php](http://www.lookpolymers.com/polymer_Reliance-Industries-Repol-R110MK-Polypropylene.php)

Physical Properties	Metric	English	Comments
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 230 °C	12 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.0 MPa	4060 psi	50mm/min; ASTM D638
Elongation at Yield	12 %	12 %	50mm/min; ASTM D638
Flexural Modulus	1.30 GPa	189 ksi	1% secant; ASTM D790A
Izod Impact, Notched	0.600 J/cm @Temperature 23.0 °C	1.12 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	150 °C	302 °F	DSC second heating; ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China