Reltek BONDiT[™] A-3 Bonding Agent, Primer and Adhesive

Category : Polymer , Adhesive , Thermoset

Material Notes:

Key Properties: Adhesion promoter and primer for coatings, sealants and adhesives on metals, glass and ceramic.Exceptional moisture and high pH resistance.Outstanding harsh environment protection and cathodic corrosion protection when used with the B-4811.Applications: Exceptional corrosion and chemical protection. Promotes adhesion and provides primer protection on most metals, ceramic and glass (including sapphire), most elastomers (including silicon) and low surface energy substrates. Functional for a wide range of overmold materials, paints, coatings, encapsulates. High thermal stability (250°C) and chemical resistance. Suitable for bonding semiconductor material. Used as adhesive for very thin bond lines (½ mil) such as for glass-to-glass and glass-to-polyethylene bonding. Compatible for use with BONDIT B-4X epoxy series. Ambient cure 60 min or accelerated thermal cure. Water white to slight amber.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reltek-BONDiT-A-3-Bonding-Agent-Primer-and-Adhesive.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.018 - 1.038 g/cc	1.018 - 1.038 g/cc	ASTM D1298
Viscosity Measurement	4.5 - 8.5	4.5 - 8.5	ASTM D445

Thermal Properties	Metric	English	Comments	
Maximum Service Temperature, Air	200 °C	392 °F		

Optical Properties	Metric	English	Comments
Refractive Index	1.442 - 1.448	1.442 - 1.448	ASTM D1218
Processing Properties	Metric	English	Comments
Cure Time	5.00 min	0.0833 hour	
	@Temperature 150 °C	@Temperature 302 °F	
Descriptive Properties	Value		Comments
Color	Clear with s		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers



Address : United North Road 215, Fengxian District, Shanghai City, China