

## Reltek BONDiT™ B-46CAT Adhesive and Sealant

Category : Polymer , Adhesive

**Material Notes:**

**Key Properties**Excellent adhesion to low surface energy plastics without primer or surface preparation.**Applications**Very high flexibility, 500% elongation, emphasizing high tack for un-abraded substrates and plastic films, including Teflon, with accelerated thermal cure: set time of 10 minutes at 200°F. Excellent for volume production in sealing cross linked polyethylene cable for high environmental resistance in automotive applications. Ambient cure 36 hours.**Information provided by Reltek LLC**

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Reltek-BONDiT-B-46CAT-Adhesive-and-Sealant.php](http://www.lookpolymers.com/polymer_Reltek-BONDiT-B-46CAT-Adhesive-and-Sealant.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	A
	1.42 g/cc	1.42 g/cc	B
Moisture Absorption at Equilibrium	<= 1.0 %	<= 1.0 %	
Viscosity	7000 cP	7000 cP	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Color	Clear with haze/slight amber	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China