

Reltek BONDiT™ HM-505 Coating, Sealant, Adhesive System

Category : Polymer , Adhesive

Material Notes:

Information provided by Reltek LLC

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reltek-BONDiT-HM-505-Coating-Sealant-Adhesive-System.php

Physical Properties	Metric	English	Comments
Density	0.955 g/cc	0.0345 lb/in ³	
Moisture Absorption at Equilibrium	0.040 % @Temperature 40.0 °C	0.040 % @Temperature 104 °F	100% RH
Water Vapor Transmission	<= 35.7 g/m ² /day @Temperature 38.0 °C	<= 2.30 g/100 in ² /day @Temperature 100 °F	ASTM E-96
Oxygen Transmission	138 cc-mm/m ² -24hr-atm @Temperature 23.0 °C	350 cc-mil/100 in ² -24hr-atm @Temperature 73.4 °F	ASTM D1434
Viscosity	850 cP	850 cP	
Environmental Stress Crack Resistance	>= 200 hour	>= 200 hour	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	42	42	ASTM D2240
Tensile Strength at Break	6.21 MPa	900 psi	ASTM D638
Elongation at Break	350 %	350 %	ASTM D638
2% Secant Modulus	0.0221 GPa	3.20 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Crystallization Temperature	75.0 °C	167 °F	
Brittleness Temperature	-23.0 °C	-9.40 °F	ASTM D746

Descriptive Properties	Value	Comments
Approximate reverse impact	24	
Color	Clear	

Fungal Resistance Descriptive Properties	No Growth Value	Comments
Insulation Resistance (V/mil)	500	
Thermal Shock	No effect	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China