

## Resin Technology Group DPE110698-1 Two component Potting Compound

Category : Polymer , Adhesive , Thermoset

**Material Notes:**

Resin Technology Group DPE110698-1 Two component Potting Compound Clear, fire retardant, low viscosity potting compound.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Resin-Technology-Group-DPE110698-1-Two-component-Potting-Compound.php](http://www.lookpolymers.com/polymer_Resin-Technology-Group-DPE110698-1-Two-component-Potting-Compound.php)

Physical Properties	Metric	English	Comments
Viscosity	<= 1000 cP	<= 1000 cP	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 120 min	1.00 - 2.00 hour	
	@Temperature 120 °C	@Temperature 248 °F	
Pot Life	120 min	120 min	
	120 min	120 min	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China