

## Resinlab® CYNERGY CA6211 Adhesive

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

### Material Notes:

Description: The CYNERGY 6200 SERIES products are for use in demanding applications where very fast cure speeds are required. Also used when difficult to bond and acidic surfaces are used such as EPDM, plasticized materials such as PVC and wood. Application: The CYNERGY SERIES of the cyanoacrylates should be applied in small amounts to one surface only. The parts should then be mated together under slight pressure. This causes the adhesive to spread out into a thin film and assures optimum adhesive performance. The pressure need only be applied for several seconds. The CYNERGY SERIES cures rapidly allowing for bonded parts to be handled within 10 to 60 seconds for most applications. Full cure is normally within 24 hours. Information Provided by Resinlab L.L.C., an Ellsworth Adhesives Company.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Resinlab-CYNERGY-CA6211-Adhesive.php](http://www.lookpolymers.com/polymer_Resinlab-CYNERGY-CA6211-Adhesive.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	
Viscosity	200 cP	200 cP	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	19.3 MPa	2800 psi	
Adhesive Bond Strength	29.0 MPa	4200 psi	Steel lap shear

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	93.3 °C	200 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	>= 0.167 min	>= 0.00278 hour	Fixture
	480 min	8.00 hour	Full cure

Descriptive Properties	Value	Comments
Base	Ethyl	
Color	Clear	
Gap Fill (mil)	6	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China