

**Resinlab® CYNERGY CA6502 Adhesive**

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

**Material Notes:**

**Description:** The CYNERGY 6500 SERIES are black, highly toughened, high peel strength products ideal for bonding dissimilar materials with excellent performance on a wide range of surfaces. They impart superior vibration, impact and thermal cycling resistance making them ideal for high stress applications. **Application:** The CYNERGY SERIES of the cyanoacrylates should be applied in small amounts to one surface only. The parts should then be mated together under slight pressure. This causes the adhesive to spread out into a thin film and assures optimum adhesive performance. The pressure need only be applied for several seconds. The CYNERGY SERIES cures rapidly allowing for bonded parts to be handled within 10 to 60 seconds for most applications. Full cure is normally within 24 hours. **Information Provided by Resinlab L.L.C., an Ellsworth Adhesives Company.**

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Resinlab-CYNERGY-CA6502-Adhesive.php](http://www.lookpolymers.com/polymer_Resinlab-CYNERGY-CA6502-Adhesive.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	
Viscosity	1000 cP	1000 cP	

Mechanical Properties	Metric	English	Comments
Shear Strength	25.9 MPa	3750 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	121 °C	250 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	>= 0.200 min	>= 0.00333 hour	Fixture
	480 min	8.00 hour	Full cure

Descriptive Properties	Value	Comments
Base	Ethyl	
Color	Black	
Gap Fill (mil)	9	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China