

Resinlab® CYNERGY CA6807 Adhesive

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

Material Notes:

Description: The CYNERGY 6800 SERIES are clear, high strength products ideal for bonding dissimilar materials with excellent performance on a wide range of surfaces. This series of products has USP Class VI Certification and are commonly used in assembling medical devices. Application: The CYNERGY SERIES of the cyanoacrylates should be applied in small amounts to one surface only. The parts should then be mated together under slight pressure. This causes the adhesive to spread out into a thin film and assures optimum adhesive performance. The pressure need only be applied for several seconds. The CYNERGY SERIES cures rapidly allowing for bonded parts to be handled within 10 to 60 seconds for most applications. Full cure is normally within 24 hours. Information Provided by Resinlab L.L.C., an Ellsworth Adhesives Company.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resinlab-CYNERGY-CA6807-Adhesive.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity | 1.09 g/cc | 1.09 g/cc | |
| Viscosity | 500 cP | 500 cP | |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|----------|----------|-----------------|
| Tensile Strength, Yield | 18.6 MPa | 2700 psi | |
| Adhesive Bond Strength | 29.6 MPa | 4300 psi | Steel lap shear |

| Thermal Properties | Metric | English | Comments | |
|----------------------------------|----------|----------|----------|--|
| Maximum Service Temperature, Air | 93.3 °C | 200 °F | | |
| Minimum Service Temperature, Air | -53.9 °C | -65.0 °F | | |

| Processing Properties | Metric | English | Comments |
|-----------------------|--------------|-----------------|-----------|
| Cure Time | >= 0.167 min | >= 0.00278 hour | Fixture |
| | 480 min | 8.00 hour | Full cure |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Base | Ethyl | |
| Color | Clear | |
| Gap Fill (mil) | 7 | |



Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China