

Resinlab® UR3010 Clear Polyurethane Potting System

Category : Polymer , Adhesive , Thermoset , Polyurethane, TS , Thermoset Polyurethane, Adhesive

Material Notes:

Resinlab™ UR 3010 Clear is a, two component, room temperature curing polyurethane potting system. It is designed to cure completely at room temperature. UR 3010 provides excellent environmental protection giving very good resistance to water, salt spray, inorganic acids and bases, and most organic solvents, while maintaining tenacious adhesion to various metals, plastics and other common assembly materials. UR 3010 Clear is an unfilled system that has a high degree of flexibility at temperatures as low as –40C. It provides excellent moisture resistance and can withstand 125°C continuous operation. Excursions to 150C for < 24 hours have no detectable effect on hardness or produces measureable weight loss. It also has a low viscosity, which facilitates flow and penetration into difficult areas. This product was formulated to a convenient mixing ratio of 1 to 1 by volume. It is well suited to automated meter mix operations. UR 3010 Clear is a DOT non-hazardous material and contains no TDI, MOCA, or other reportable substances. Part B is moisture sensitive and must be kept away from atmospheric moisture during storage. After opening a sealed container, thoroughly purge the remaining air space with dry nitrogen (or equivalent) before closing the container. Information Provided by Resinlab L.L.C., an Ellsworth Adhesives Company.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resinlab-UR3010-Clear-Polyurethane-Potting-System.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	Part A
	1.04 g/cc	1.04 g/cc	Mixed
	1.10 g/cc	1.10 g/cc	Part B
Viscosity	275 cP	275 cP	Part B
	615 cP	615 cP	Mixed
	1000 cP	1000 cP	Part A

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	
Tensile Strength, Yield	0.552 MPa	80.0 psi	
	1.72 MPa	250 psi	at 100%
Elongation at Break	60 %	60 %	

Thermal Properties	Metric	English	Comments
CTE, linear	200 µm/m-°C	111 µin/in-°F	

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Transmission Visible Optical Properties	90 % Metric	90 % English	clear: thickness not quantified Comments
--	----------------	-----------------	---

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.00e+15 ohm-cm	3.00e+15 ohm-cm	
Dielectric Constant	3.96 @Frequency 100 Hz, Temperature 25.0 °C	3.96 @Frequency 100 Hz, Temperature 77.0 °F	
Dielectric Strength	19.7 kV/mm	500 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min @Temperature 85.0 °C	1.00 hour @Temperature 185 °F	
	1440 min @Temperature 25.0 °C	24.0 hour @Temperature 77.0 °F	
Pot Life	30 - 45 min	30 - 45 min	Mass: 100g

Descriptive Properties	Value	Comments
Color	Clear	
Fungus Resistance	Excellent	
Mix Ratio	1:1	Volume
	88:100	Weight

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China