

Resinoid 2016P Phenolic Molding, Fabric Reinforced

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic , Phenolic, Novolac, Fabric Filled

Material Notes:

Data provided by the manufacturer. The Resinoid 2000 organic fiber reinforced series compounds feature mechanical strength, dimensional stability, and shock resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resinoid-2016P-Phenolic-Molding-Fabric-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ASTM D792A
Water Absorption	0.80 %	0.80 %	24 hours R.T. ASTM D570
Linear Mold Shrinkage	0.0025 cm/cm	0.0025 in/in	Positive Mold; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell E	76	76	ASTM D785
Hardness, Rockwell M	108	108	ASTM D785
Tensile Strength, Ultimate	58.0 MPa	8410 psi	ASTM D651
Flexural Strength	83.0 MPa	12000 psi	ASTM D790
Compressive Strength	159 MPa	23100 psi	ASTM D695
Izod Impact, Notched	0.683 J/cm	1.28 ft-lb/in	ASTM D256A
Charpy Impact, Notched	0.683 J/cm ²	3.25 ft-lb/in ²	J/cm; Notched; ASTM D256B

Thermal Properties	Metric	English	Comments
CTE, linear	40.0 $\mu\text{m}/\text{m}\cdot\text{°C}$ @Temperature 20.0 °C	22.2 $\mu\text{in}/\text{in}\cdot\text{°F}$ @Temperature 68.0 °F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	238 °C	460 °F	ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Dielectric Strength	9.60 kV/mm	244 kV/in	Short Time; Dry; ASTM D149
Arc Resistance	115 sec	115 sec	ASTM D495

Processing Properties	Metric	English	Comments
Mold Temperature	150 - 175 °C	302 - 347 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China