

Resirene Resirene® 7600 Super High Impact Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Features:Medium FlowSuper High ImpactEasy ProcessingHigh ProductivityFDA Rating: 21 CFR

177.1640Applications:InjectionToysCompounds and Master BatchPrintersComputersRemote ControlsInformation provided by US distributor Calsak Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resirene-Resirene-7600-Super-High-Impact-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	ASTM D955
Melt Flow	4.5 g/10 min @Load 5.00 kg, Temperature 200 °C	4.5 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	20.0 MPa	2900 psi	ASTM D638
Tensile Strength, Yield	24.8 MPa	3600 psi	ASTM D638
Elongation at Break	64 %	64 %	ASTM D638
Tensile Modulus	2.103 GPa	305.0 ksi	ASTM D638
Izod Impact, Notched	0.910 J/cm	1.70 ft-lb/in	0.5 in.; ASTM D256
	1.12 J/cm	2.10 ft-lb/in	0.125 in.; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	82.0 °C	180 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China