

Resistalloy International Fecralloy™ 134 Electrical Resistance Steel

Category : Metal , Electronic/Magnetic Alloy , Ferrous Metal , Stainless Steel , Superalloy

Material Notes:

Ferritic stainless steel with aluminum. Available as wire and strip. Used mainly for electrical elements in both industrial and domestic applications. Industrial applications vary from small laboratory kilns to heavy-duty heat-treatment furnaces under all types of atmospheres. "Fecralloy" is an Fe-Cr-Al steel containing "yttrium" is a versatile alloy and is suitable for use over a wide range up to 1300°C. The "yttrium" is the key to its longer high temperature life, having greater oxidation resistance and form stability over other resistance alloys. "Fecralloy" is the registered trademark of the UK Atomic Energy Authority (Now AEA Technology, Harwell). Information provided by Resistalloy International Limited.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resistalloy-International-Fecralloy-134-Electrical-Resistance-Steel.php

Physical Properties	Metric	English	Comments
Density	7.28 g/cc	0.263 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	230	230	
Tensile Strength, Ultimate	750 MPa	109000 psi	
	30.0 MPa	4350 psi	
	@Temperature 900 °C	@Temperature 1650 °F	
Tensile Strength, Yield	550 MPa	79800 psi	
Elongation at Break	16 - 20 %	16 - 20 %	
	@Thickness 50.0 mm	@Thickness 1.97 in	

Thermal Properties	Metric	English	Comments
CTE, linear	11.0 µm/m-°C	6.11 µin/in-°F	
	@Temperature 20.0 - 250 °C	@Temperature 68.0 - 482 °F	
	12.0 µm/m-°C	6.67 µin/in-°F	
	@Temperature 20.0 - 500 °C	@Temperature 68.0 - 932 °F	
	15.0 µm/m-°C	8.33 µin/in-°F	
	@Temperature 20.0 - 1000 °C	@Temperature 68.0 - 1830 °F	
Specific Heat Capacity	0.480 J/g-°C	0.115 BTU/lb-°F	

Thermal Properties	Metric	English	Comments
Melting Point	1500 °C	2730 °F	
Maximum Service Temperature, Air	1100 °C	2010 °F	

Optical Properties	Metric	English	Comments
Emissivity (0-1)	0.70	0.70	Fully Oxidized

Component Elements Properties	Metric	English	Comments
Aluminum, Al	4.3 %	4.3 %	
Chromium, Cr	15 %	15 %	
Iron, Fe	81 %	81 %	As remainder

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000126 ohm-cm	0.000126 ohm-cm	Temperature Factor is 1.10 at 800°C (1470°F). Temperature Factor is 1.11 at 1000°C (1830°F).
Curie Temperature	600 °C	1110 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China