

RheTech Products FRP300-00 20% Talc Reinforced Polypropylene Copolymer, Flame Retardant, Natural

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler

Material Notes:

Applications: Electrical component housings Injection molding conditions reported in table. Information provided by RheTech Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_RheTech-Products-FRP300-00-20-Talc-Reinforced-Polypropylene-Copolymer-Flame-Retardant-Natural.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	23/23°C; ASTM D792
Filler Content	20 %	20 %	ASTM D5630
Linear Mold Shrinkage	0.0118 cm/cm	0.0118 in/in	ASTM D955
Melt Flow	22 g/10 min @Load 2.16 kg, Temperature 230 °C	22 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	70	70	ASTM D2240
Tensile Strength at Break	26.2 MPa	3800 psi	2 in/min; ASTM D638
Flexural Modulus	2.21 GPa	320 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.267 J/cm @Temperature 23.0 °C	0.500 ft-lb/in @Temperature 73.4 °F	ASTM D256
Gardner Impact	2.37 J	1.75 ft-lb	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	220 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.6 °C	150 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	191 - 199 °C	375 - 390 °F	
Middle Barrel Temperature	199 - 210 °C	390 - 410 °F	
Front Barrel Temperature	199 - 210 °C	390 - 410 °F	

Processing Properties	Metric	English	Comments
Mold Temperature	23.9 - 35.0 °C	75.0 - 95.0 °F	
Drying Temperature	51.7 - 65.6 °C	125 - 150 °F	
Dry Time	1 - 2 hour	1 - 2 hour	
Moisture Content	<= 0.050 %	<= 0.050 %	Recommended
Injection Pressure	2.76 - 8.27 MPa	400 - 1200 psi	
Hold Pressure	2.07 - 6.89 MPa	300 - 1000 psi	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China