

RheTech Products HP501-00 High Performance Polypropylene Copolymer, Non-UV Stabilized, Natural

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Applications: Battery traysInterior TrimInjection molding conditions reported in table.Information provided by RheTech Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_RheTech-Products-HP501-00-High-Performance-Polypropylene-Copolymer-Non-UV-Stabilized-Natural.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	23/23°C; ASTM D792
Filler Content	0.00 %	0.00 %	ASTM D5630
Linear Mold Shrinkage	0.0145 cm/cm	0.0145 in/in	ASTM D955
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 230 °C	35 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	73	73	ASTM D2240
Tensile Strength at Break	32.4 MPa	4700 psi	2 in/min; ASTM D638
Flexural Modulus	1.41 GPa	205 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.374 J/cm @Temperature 23.0 °C	0.700 ft-lb/in @Temperature 73.4 °F	ASTM D256
Gardner Impact	1.25 J	0.920 ft-lb	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	101 °C	214 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	57.8 °C	136 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	188 - 216 °C	370 - 420 °F	
Middle Barrel Temperature	193 - 221 °C	380 - 430 °F	
Front Barrel Temperature	199 - 227 °C	390 - 440 °F	

Processing Properties	Metric ^{16 °C}	English ^{20 °F}	Comments
Mold Temperature	26.7 - 48.9 °C	80.0 - 120 °F	
Drying Temperature	65.6 - 82.2 °C	150 - 180 °F	
Dry Time	1 - 2 hour	1 - 2 hour	
Moisture Content	<= 0.050 %	<= 0.050 %	Recommended
Injection Pressure	2.76 - 10.3 MPa	400 - 1500 psi	
Hold Pressure	2.07 - 8.27 MPa	300 - 1200 psi	
Back Pressure	0.345 - 1.03 MPa	50.0 - 150 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China