

## RheTech Products M15P100-01A 15% Mica Reinforced Polypropylene, Black

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Mica Filler

### Material Notes:

Applications: Fan shrouds Air ducts Electronics Injection molding conditions reported in table. Information provided by RheTech Products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_RheTech-Products-M15P100-01A-15-Mica-Reinforced-Polypropylene-Black.php](http://www.lookpolymers.com/polymer_RheTech-Products-M15P100-01A-15-Mica-Reinforced-Polypropylene-Black.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.02 g/cc	1.02 g/cc	23/23°C; ASTM D792
Filler Content	15 %	15 %	ASTM D5630
Linear Mold Shrinkage	0.0115 cm/cm	0.0115 in/in	ASTM D955
Melt Flow	17 g/10 min @Load 2.16 kg, Temperature 230 °C	17 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68	68	ASTM D2240
Tensile Strength at Break	32.4 MPa	4700 psi	2 in/min; ASTM D638
Flexural Modulus	2.41 GPa	350 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.267 J/cm @Temperature 23.0 °C	0.500 ft-lb/in @Temperature 73.4 °F	ASTM D256
Gardner Impact	0.339 J	0.250 ft-lb	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	124 °C	255 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.6 °C	150 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	193 - 221 °C	380 - 430 °F	
Middle Barrel Temperature	199 - 227 °C	390 - 440 °F	
Front Barrel Temperature	204 - 232 °C	400 - 450 °F	
Nozzle Temperature	210 - 221 °C	410 - 430 °F	

Processing Properties	Metric <sup>25.7 - 48.9 °C</sup>	English <sup>80.0 - 120 °F</sup>	Comments
Drying Temperature	65.6 - 82.2 °C	150 - 180 °F	
Dry Time	1 - 2 hour	1 - 2 hour	
Moisture Content	<= 0.050 %	<= 0.050 %	Recommended
Injection Pressure	2.76 - 10.3 MPa	400 - 1500 psi	
Hold Pressure	2.07 - 8.27 MPa	300 - 1200 psi	
Back Pressure	0.345 - 1.03 MPa	50.0 - 150 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China