

RheTech Products T30P100-00 30% Talc Reinforced Polypropylene, Natural

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Applications: Headlamp housingsI/P componentsHVAC ductworkInjection molding conditions reported in table.Information provided by RheTech Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_RheTech-Products-T30P100-00-30-Talc-Reinforced-Polypropylene-Natural.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	23/23°C; ASTM D792
Filler Content	30 %	30 %	ASTM D5630
Linear Mold Shrinkage	0.0105 cm/cm	0.0105 in/in	ASTM D955
Melt Flow	17 g/10 min @Load 2.16 kg, Temperature 230 °C	17 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75	75	ASTM D2240
Tensile Strength at Break	27.6 MPa	4000 psi	2 in/min; ASTM D638
Flexural Modulus	2.90 GPa	420 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.267 J/cm @Temperature 23.0 °C	0.500 ft-lb/in @Temperature 73.4 °F	ASTM D256
Gardner Impact	0.790 J	0.583 ft-lb	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	126 °C	258 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	71.1 °C	160 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	204 - 232 °C	400 - 450 °F	
Middle Barrel Temperature	210 - 238 °C	410 - 460 °F	
Front Barrel Temperature	216 - 243 °C	420 - 470 °F	

Nozzle Temperature Processing Properties	221 - 232 °C Metric	430 - 450 °F English	Comments
Mold Temperature	26.7 - 48.9 °C	80.0 - 120 °F	
Drying Temperature	65.6 - 82.2 °C	150 - 180 °F	
Dry Time	1 - 2 hour	1 - 2 hour	
Moisture Content	<= 0.050 %	<= 0.050 %	Recommended
Injection Pressure	55.2 - 103 MPa	8000 - 15000 psi	
Hold Pressure	27.6 - 51.7 MPa	4000 - 7500 psi	
Back Pressure	0.345 - 1.03 MPa	50.0 - 150 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China