

Rogers Corporation Poron® Shock Seal™ 4790-79-20 Urethane Foam, Industrial Grade

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced

Material Notes:

Thickness: 0.062"- 0.188"Color: BlackInformation provided by Rogers Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Rogers-Corporation-Poron-Shock-Seal-4790-79-20-Urethane-Foam-Industrial-Grade.php

Physical Properties	Metric	English	Comments
Density	0.320 g/cc	0.0116 lb/in ³	ASTM D3574-95 Test A
Water Absorption	10 % @Time 7200 sec	10 % @Time 2.00 hour	Immersion; ASTM D570
Thickness	1570 - 4780 microns	62.0 - 188 mil	Range of Thicknesses Available

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 0.689 MPa	>= 100 psi	ASTM D3574-75 Test E
Elongation at Break	>= 145 %	>= 145 %	ASTM D3574-75 Test E
Compressive Yield Strength	0.0276 - 0.110 MPa @Strain 25.0 %	4.00 - 16.0 psi @Strain 25.0 %	0.2"/min. strain rate
Tear Strength	>= 1.80 kN/m	>= 10.3 pli	ASTM D642-91 Die C
Compression Set	<= 5.0 % @Temperature 23.0 °C	<= 5.0 % @Temperature 73.4 °F	ASTM D3574-95 Test D
	<= 10 % @Temperature 70.0 °C	<= 10 % @Temperature 158 °F	ASTM D3574-95 Test D

Descriptive Properties	Value	Comments
Flammability Test	pass	MVSS 302; 0.062 in.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China