

## Rogers Corporation R/bak® U1A Cushion Mounting Material, Unsupported with Single-sided Acrylic Adhesive

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced

### Material Notes:

R/bak® materials are high-density, open cell, polyurethane foams used to build thickness on the cylinder, provide cushioning and absorb vibration in the Flexographic printing process. The use of R/bak cushioning materials results in uniform quality printing over long run conditions. R/bak materials are available in a variety of length and thickness configurations. R/bak U1A is recommended for cylinder build-up, spot cushioning and spot coating applications for higher print quality. Information provided by Rogers Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Rogers-Corporation-Rbak-U1A-Cushion-Mounting-Material-Unsupported-with-Single-sided-Acrylic-Adhesive.php](http://www.lookpolymers.com/polymer_Rogers-Corporation-Rbak-U1A-Cushion-Mounting-Material-Unsupported-with-Single-sided-Acrylic-Adhesive.php)

Physical Properties	Metric	English	Comments
Density	0.320 g/cc	0.0116 lb/in <sup>3</sup>	ASTM D3574-95 Test A
Water Absorption	2.0 %	2.0 %	AMS 3568
	5.0 %	5.0 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	16	16	ASTM D2240
Hardness, Shore O	24	24	ASTM D2240
Tensile Strength	>= 0.827 MPa	>= 120 psi	ASTM D3573 Test E
Elongation at Break	>= 100 %	>= 100 %	ASTM D3573 Test E
Compressive Yield Strength	0.124 MPa @Strain 25.0 %	18.0 psi @Strain 25.0 %	
Tear Strength	>= 1.80 kN/m	>= 10.3 pli	ASTM D624, Die C
Compression Set	<= 1.3 % @Temperature 23.0 °C	<= 1.3 % @Temperature 73.4 °F	ASTM D1667
	<= 3.3 % @Temperature 70.0 °C	<= 3.3 % @Temperature 158 °F	ASTM D3574

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**