

SABIC Innovative Plastics Cycolac® INP581 ABS+SAN

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

High flow, low molecular weight SAN. Can be used as compounding additives for polymer blends. Can be blended with high rubber graft modifier resins to produce customized ABS properties. Suitable for direct weather exposure. Provides excellent flow for demanding injection molding applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycolac-INP581-ABSSAN.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Density	1.07 g/cc	0.0387 lb/in ³	ISO 1183
Melt Flow	37.7 g/10 min	37.7 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	
	98 g/10 min	98 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength at Break	60.0 MPa	8700 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	48.0 MPa	6960 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	1.9 %	1.9 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	1.5 %	1.5 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	4.08 GPa	592 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	36.0 MPa	5220 psi	2 mm/min; ISO 178
	66.0 MPa	9570 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	3.44 GPa	499 ksi	1.3 mm/min, 50 mm span; ASTM D790
	3.52 GPa	511 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.230 J/cm	0.431 ft-lb/in	ASTM D256
	0.120 J/cm	0.225 ft-lb/in	

Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	ASTM D256 Comments
Izod Impact, Notched (ISO)	1.00 kJ/m ²	0.476 ft-lb/in ²	80*10*4; ISO 180/1A
	1.00 kJ/m ² @Temperature -30.0 °C	0.476 ft-lb/in ² @Temperature -22.0 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	0.100 J/cm ²	0.476 ft-lb/in ²	ISO 179/2C

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	97.0 °C @Thickness 3.20 mm	207 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	82.0 °C	180 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	86.0 °C @Thickness 3.20 mm	187 °F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	102 °C	216 °F	Rate B/50; ISO 306
	104 °C	219 °F	Rate B/120; ISO 306

Optical Properties	Metric	English	Comments
Yellow Index	1.0 %	1.0 %	ASTM D1925

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China