

SABIC Innovative Plastics Cycolac® MG29 ABS (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Super high impact ABS. Good low temperature toughness. High gloss.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycolac-MG29-ABS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Viscosity	280000 cP	280000 cP	Melt Viscosity, 240°C, 1000 sec-1; ASTM D3825
Linear Mold Shrinkage, Flow	0.0050 - 0.0080 cm/cm @Thickness 3.20 mm	0.0050 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	1.2 g/10 min @Load 3.80 kg, Temperature 230 °C	1.2 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D1238
	10 g/10 min @Load 10.0 kg, Temperature 220 °C	10 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	31.0 MPa	4500 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	38.0 MPa	5510 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	26 %	26 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	2.4 %	2.4 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	1.99 GPa	289 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	64.0 MPa	9280 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.06 GPa	299 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	4.53 J/cm	8.49 ft-lb/in	ASTM D256
Dart Drop, Total Energy	28.0 J @Temperature 23.0 °C	20.7 ft-lb @Temperature 73.4 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	95.4 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ @Temperature -40.0 - 40.0 $^\circ\text{C}$	53.0 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ @Temperature -40.0 - 104 $^\circ\text{F}$	ASTM E 831
CTE, linear, Transverse to Flow	93.6 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ @Temperature -40.0 - 40.0 $^\circ\text{C}$	52.0 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ @Temperature -40.0 - 104 $^\circ\text{F}$	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	96.0 $^\circ\text{C}$ @Thickness 3.20 mm	205 $^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	81.0 $^\circ\text{C}$ @Thickness 3.20 mm	178 $^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	98.0 $^\circ\text{C}$	208 $^\circ\text{F}$	Rate B/50; ASTM D1525
UL RTI, Electrical	60.0 $^\circ\text{C}$	140 $^\circ\text{F}$	UL 746B
UL RTI, Mechanical with Impact	60.0 $^\circ\text{C}$	140 $^\circ\text{F}$	UL 746B
UL RTI, Mechanical without Impact	60.0 $^\circ\text{C}$	140 $^\circ\text{F}$	UL 746B
Flammability, UL94	HB @Thickness 1.52 mm	HB @Thickness 0.0598 in	UL 94

Electrical Properties	Metric	English	Comments
Arc Resistance	120 - 180 sec	120 - 180 sec	Tungsten; ASTM D495
Comparative Tracking Index	≥ 600 V	≥ 600 V	UL 746A
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	0.000 - 10.0 mm/min	0.000 - 0.394 in/min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China