

SABIC Innovative Plastics Cycloy® C1110 PC+ABS (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

High impact and ductility at 73F (23C) and -20F (-29C).

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycloy-C1110-PCABS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Moisture Absorption at Equilibrium	0.40 %	0.40 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	2.5 g/10 min	2.5 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	
	8.0 g/10 min	8.0 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 260 °C	@Load 8.38 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	56.0 MPa	8120 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	150 %	150 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	5.0 %	5.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.20 GPa	319 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	86.0 MPa	12500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	6.40 J/cm	12.0 ft-lb/in	ASTM D256
	5.34 J/cm	10.0 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	40.0 J	29.5 ft-lb	

Dart Drop, Total Energy Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	ASTM D3763 Comments
	54.0 J	39.8 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 µm/m-°C @Temperature -40.0 - 40.0 °C	40.0 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	123 °C @Thickness 3.20 mm	253 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	107 °C @Thickness 3.20 mm	225 °F @Thickness 0.126 in	unannealed; ASTM D648
UL RTI, Electrical	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical with Impact	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical without Impact	60.0 °C	140 °F	UL 746B
Flammability, UL94	HB @Thickness 1.21 mm	HB @Thickness 0.0476 in	UL 94

Electrical Properties	Metric	English	Comments
Arc Resistance	120 - 180 sec	120 - 180 sec	Tungsten; ASTM D495
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL 746A
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	10.0 - 25.4 mm/min	0.394 - 1.00 in/min	UL 746A

Descriptive Properties	Value	Comments
UV-light, water exposure/immersion	F2	UL 746C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China