

SABIC Innovative Plastics Cycloy® CU1650 PC+ABS (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

UV stabilized, non-FR PC/ABS of excellent flow and impact performance This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycloy-CU1650-PCABS-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D 792
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.15 %	0.15 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.40 % @Temperature 23.0 °C	0.40 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 260 °C	8.0 g/10 min @Load 4.76 lb, Temperature 500 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	25 g/10 min @Load 5.00 kg, Temperature 260 °C	25 g/10 min @Load 11.0 lb, Temperature 500 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	28 g/10 min @Load 5.00 kg, Temperature 260 °C	28 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	53.0 MPa	7690 psi	Type I, 50 mm/min; ASTM D 638
	53.0 MPa	7690 psi	50 mm/min; ISO 527
Tensile Strength, Yield	54.0 MPa	7830 psi	Type I, 50 mm/min; ASTM D 638
	54.0 MPa	7830 psi	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
	120 %	120 %	50 mm/min; ISO 527
Elongation at Yield	4.5 %	4.5 %	Type I, 50 mm/min; ASTM D 638
	4.5 %	4.5 %	50 mm/min; ISO 527
Tensile Modulus	2.25 GPa	326 ksi	1 mm/min; ISO 527
	2.30 GPa	334 ksi	5 mm/min; ASTM D 638
Flexural Yield Strength	80.0 MPa	11600 psi	2 mm/min; ISO 178
	89.0 MPa	12900 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.20 GPa	319 ksi	2 mm/min; ISO 178
	2.30 GPa	334 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	4.00 J/cm	7.49 ft-lb/in	ASTM D 256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	5.90 J/cm	11.1 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched (ISO)	30.0 kJ/m ²	14.3 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	65.0 kJ/m ²	30.9 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	3.00 J/cm ²	14.3 ft-lb/in ²	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.50 J/cm ²	30.9 ft-lb/in ²	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	55.0 J	40.6 ft-lb	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	

Thermal Properties	Metric @Temperature -40.0 - 40.0 °C	English @Temperature -40.0 - 104 °F	ISO 11359-2 Comments
CTE, linear, Transverse to Flow	70.0 µm/m-°C @Temperature -40.0 - 40.0 °C	38.9 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
	80.0 µm/m-°C @Temperature -40.0 - 40.0 °C	44.4 µin/in-°F @Temperature -40.0 - 104 °F	ISO 11359-2
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	126 °C	259 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	105 °C	221 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	107 °C @Thickness 3.20 mm	225 °F @Thickness 0.126 in	unannealed; ASTM D 648
Vicat Softening Point	126 °C	259 °F	Rate B/50; ASTM D 1525
	126 °C	259 °F	Rate B/50; ISO 306
	127 °C	261 °F	Rate B/120; ISO 306
UL RTI, Electrical	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical with Impact	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical without Impact	60.0 °C	140 °F	UL 746B
Glow Wire Test	750 °C @Thickness 3.00 mm	1380 °F @Thickness 0.118 in	Glow Wire Ignitability Temperature; IEC 60695-2-13

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Strength	17.0 kV/mm @Thickness 3.20 mm	432 kV/in @Thickness 0.126 in	in oil; IEC 60243-1
	25.0 kV/mm @Thickness 1.60 mm	635 kV/in @Thickness 0.0630 in	in oil; IEC 60243-1
	35.0 kV/mm @Thickness 0.800 mm	889 kV/in @Thickness 0.0315 in	in oil; IEC 60243-1

Descriptive Properties	Value	Comments
Ball Pressure Test, 75°C +/- 2°C	Pass	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China